

innovus

Decorative Products

INNOVUS DP MDF FIRE X CARB2/EPA

Decorative Surfaced Panel Medium Density Fiberboard with improved fire behavior for use in dry conditions

DESCRIPTION -

INNOVUS DP MDF FIRE X CARB2/EPA is a surfaced fibreboard with improved fire reaction behaviour, suitable for non-structural applications in dry conditions. Its surface is easy to clean and scratch & stain resistant.

INNOVUS DP MDF FIRE X CARB2/EPA uses core board certified according to the rules of the official California Air Resources Board (CARB).

Regarding reaction to fire and according to EN 13986, INNOVUS DP MDF FIRE X CARB2/EPA is classified as B-s1, d0 (Euroclasses definition by EN 13501-1) and it is recommended for use in sectors with strict regulations on the fire performance of the materials used.

The use of INNOVUS DP MDF FIRE X CARB2/EPA contributes to reduce he combustion of an element, the spread of fire, the possible heat emissions after the combustion and to prevent or delay the spread of fire to neighbouring elements.

In addition to technical performance INNOVUS DP MDF FIRE X CARB2/EPA panels are sustainable and environmental friendly products.

For further information on available sizes and thicknesses, please see our Offer & Service Brochure.

PROPERTIES -



















SCRATCH RESISTANT

EPA TSCA TITLE VI & FIRE RETARDANT

APPLICATIONS

INNOVUS DP MDF FIRE X CARB2/EPA durability, design and versatility make it a best choice especially for public & commercial areas, fairs, but also for residential and healthcare applications.

It can also be used in combination with other materials to value engineer projects by improving costs while maintaining design integrity.











OFFICES &

RESTAURANTS & HOTELS



FURNITURE

PANELING

KITCHENS

RECOMMENDATION

INNOVUS DP MDF panels must be stored in a dry/covered building, stacked on a hard, level surface and protected from direct contact with water. Expansion and contraction in wood products is directly related to moisture content and must be considered during design and construction.

Wood based panels are biodegradable and can be recycled, follow local regulation for the disposal of residues.

To clean, simply use a cloth dampened in warm water or the usual household cleaning products. Common cleaning products or disinfectants (for example alcohol-based ones) can be used, as long as they do not contain abrasive agents, acids or strongly alkaline substances. Also, bleach or detergent products that contain high levels of chlorine should be avoided.





Decorative Products

INNOVUS DP MDF FIRE X CARB2/EPA

Decorative Surfaced Panel Medium Density Fiberboard with improved fire behavior for use in dry conditions

GENERAL CHARACTERISTICS

PROPERTY	TEST	UNIT	T	THICKNESS RANGE (mm)		
			<15	≥15 - 20	>20	
Tolerance on thickness relative to nominal value	EN 14323	mm	± 0,3	± 0,3	± 0,5	
Tolerance on thickness within the board	EN 14323	mm	< 0,6	< 0,6	< 0,6	
Tolerance on Length and Width	EN 14323	mm	± 5	± 5	± 5	
Flatness (only for balanced surfaces)	EN 14323	mm/m	-	≤ 2	≤ 2	

TECHNICAL INFORMATION

PROPERTY	TEST	UNIT	REQUIREMENTS
Resistance to scratching	EN 14323	N	≥ 1,5
Resistance to staining	EN 14323	Rating	≥ 3
Resistance to cracking	EN 14323	Rating	≥ 3
Abrasion resistance – woodgrains & fantasises	EN 14323	Class 1	IP < 50
Abrasion resistance – unicolours	EN 14323	Class 3A	IP ≥ 150
Formaldehyde emission class			E1*

^{*} uses certified substrate according to CARB 2/EPA TSCA.

INNOVUS DP MDF FIRE X CARB2/EPA are classified according to the criteria defined by EN 14322 - Wood-based panels – Melamine faced boards for interior uses - Definition, requirements and classification. For more information regarding the technical properties, please check the product Declaration of Performance (DoP).

Physical-mechanical properties differ according to the substrate used. Please check the corresponding technical data sheet for more information.

CERTIFICATIONS –

Please pay attention to certified products:



The mark of responsible forestry FSC* C104607







 $\ensuremath{\mathsf{FSC}}^{\otimes}$ and PEFC-certified products are available on request and availability.

www.sonaearauco.com

TDS.05.10.SAI.R02

All the product names and company names used in this data sheet are trade names and / or registered trademarks belonging to the respective proprietors. Any reproduction requires the express authorization of Sonae Arauco and /or the respective trademark proprietor. Sonae Arauco assumes no liability for any possible errors in this data sheet. This technical data sheet reflects the current technical specifications at the time of print and will be superseded by any new edition. The Company reserves the right to change specifications at any time without prior notification. Our detailed instructions for use must be observed. The respective building regulations must be complied with. It is important to check the material's suitability for the intended purpose.

